



# **PRODUCT WARRANTY FOR RESIDENTIAL HOUSING**

**UNI-PIER AUSTRALIA PTY LTD**



## **TERMS & CONDITIONS: 8TH FEBRUARY, 2021 V1.1**

### **Detailed Terms**

“Installation Location”; means various locations with a corrosion category limit or a specific location.

“Uni-Pier Australia”; means Uni-Pier Australia Pty Ltd ACN 131 900 546. ABN 92 131 900 546.

“Uni-Pier Australia’s Guidelines”; means the guidelines provided by Uni-Pier Australia in whatever form as may vary from time to time.

“Product”; means Hot dip galvanized flooring system or component supplied to you.

“Purchase Date”; means the date that Uni-Pier Australia supplied the Product.

“Warranty Period”; means 25 years from the purchase date. This warranty applies to the specific residence, identified in the warranty certificate, where the Uni-Pier products have been supplied and installed. The certificate must be completed in full and returned via email to Uni-Pier Australia.

### **Express Warranties**

- (a) during the Warranty Period the Product:
  - (i) will not incur red rust from corrosion loss of the metallic coating to base metal from atmospheric corrosion when the Product is exposed in internal and external environments within Australia; and
  - (ii) will perform for the purpose for which it was manufactured subject to the Limitations and Qualifications set out below;
- (b) the Product will be manufactured in accordance with AS/NZS 4680, hot-dip galvanised (zinc) coatings on fabricated ferrous articles;
- (c) the minimum thickness of the hot-dipped galvanised coating applied to the Product will be 390g/m<sup>2</sup>

### **Rights under Australian Consumer Law**

1. Clause 3 applies to You if:
  - (a) the amount paid or payable for the Product did not exceed \$40,000 (except where the Product is not of a kind ordinarily acquired for personal, domestic or household use or consumption, and Uni-Pier Australia has limited its liability in a manner permitted by the Australian Consumer Law, in which case Your rights are limited to that extent); or
  - (b) the Product is of a kind ordinarily acquired for personal, domestic or household use or consumption, unless You acquired the Product for the purpose of re-supply or the purpose of using it up or transforming it in trade or commerce.
2. Uni-Pier Australia products come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if goods fail to be of acceptable quality and the failure does not amount to a major failure.
3. The benefits given to You by this Warranty are in addition to other rights and remedies. You may have under a law in relation to the Product.

### **Limitations and Qualifications**

4. This Warranty cannot be transferred unless You are a contractor who supplied or installed the Product, in which case You may transfer this Warranty to the home owner at the Installation Location provided the transfer is effected within 12 months following the completion of the works. If the home owner of the Installation Location is comprised of joint tenants in common, then one of the joint tenants or tenants in common must be nominated as the transferee. The nominated transferee will be covered by this Warranty for the balance of the Warranty Period remaining after the date of transfer and cannot transfer any rights under this warranty to a third party.
5. This Warranty does not cover against aesthetic surface corrosion including, white corrosion products, and does not cover coating repair or after-galvanizing weld zones and/or plate fitments.
6. This Warranty does not cover corrosion loss of the metallic coating to base metal of the Product or any components of the Product wholly or partly due to an event or cause beyond the reasonable control of Uni-Pier Australia, including but not limited to:
  - (a) The storage of the Product prior to installation in a manner conducive to corrosion, including long term storage in damp and poorly ventilated conditions, or storage of the Product in contact with the ground;
  - (b) Installation of the Product or alterations, removal and re-installation of any part of the Product after its installation;
  - (c) Installation subject to unusually corrosive environments or when the Product is completely or partially immersed. Installations subject to unusually corrosive environments or where the Product is completely or partially immersed in a manner that is not approved and is not in accordance with Uni-Pier Australia’s Guidelines;



- (d) Installation where the Product is positioned in unusually wet conditions or in areas where ventilation is inadequate to eliminate or minimise condensation;
  - (e) Contact with soils, ashes fertilizers or other moisture retaining substances, chemical agents, green or wet timber or treated timber, areas in metallic contact with lead or copper or other bi-metal activity or water run-off from such materials;
  - (f) Attack from chemical agents, fumes, liquids or solids other than direct rain falling onto the Product;
  - (g) Damage sustained during transport, handling, storage or installation; and
  - (h) Accidental or intentional damage howsoever caused, and damage or defects caused by earthquakes, cyclones, storms, fire, hail, floods, and other extreme acts of God.
7. For this Warranty to be and remain effective, the following must occur:
- (a) The Installation Location must be greater than 1 kilometre from severe coastal & marine influences;
  - (b) The Installation Location must not be in an area defined as CX, C5 or C4 in accordance with Table 6.2 of AS/NZS 23 12.2 and Table 1 from AS/NZS 4680.
  - (c) Fasteners or components fixed to or used to fix the Product must be manufactured by materials approved by Uni-Pier Australia.
  - (d) The original factory finish of the Product must not be resurfaced or coated with an additional coating that is not approved and in accordance with Uni-Pier Australia's recommendations; and
  - (e) The Product must be installed, used and maintained in strict accordance with Uni-Pier Australia guidelines. Regular maintenance and cleaning is required to remove contamination, deposits and debris from the surface of the Product (particularly areas on the product not normally exposed to rain).
  - (f) The product should not be used to support decks in the wet zones around saltwater pools due to the high risk of salt saturated wet timber resulting in accelerated corrosion of the galvanised coating and structural steel.
  - (g) For house piers or stumps cast into the concrete footings, an additional barrier protection of the galvanised coating is required at the concrete interface, extending 100mm above and 250mm below the concrete surface. This must be done in accordance with the Galvanisers Association of Australia Advisory Note AN49.1 Best practice for BCA Vol 2 Part 3.4.4.4.3. Corrosion Protection. In addition, the bottom the pier should be fully encased in concrete according to the engineer's specification, and the top of the concrete slope to prevent ponding.
8. You acknowledge that Uni-Pier Australia may access the Installation Location on or prior to installation of the Product as part of the warranty registration process and/or to inspect and conduct tests as necessary at any time after a claim is made under this Warranty.
9. Subject to Uni-Pier Australia's obligations under applicable laws which cannot be excluded, modified or restricted under law (including as described in clauses 3 and 4), in the event of a valid claim under the Warranty, Uni-Pier Australia's liability to you:
- (a) Shall be limited to Uni-Pier Australia's choice of either the cost of repairing the defective piers by undertaking suitable metallic coating rectification works or replacing the defective Product with the same or equivalent Product; and
  - (b) Shall not include or extend to labour costs associated with the installation or removal of affected Product or the fixing of replacement Product; or injury or death to persons, damage to property, loss or income, profit or business or any other indirect loss arising from or caused in any way by the defective Product.
10. If Uni-Pier Australia provides You with new Products (whether of the same or equivalents Product) to replace the defective Product covered by this Warranty, the new Products will be covered by this Warranty for the remainder of its term as if the new Products were the original Products. Uni-Pier Australia will not provide You with a new Warranty in relation to the new Products provided to You in accordance with this Warranty.
11. This Warranty excludes all other warranties, conditions, offers, promises or assurances, whether express or implied, except to the extent that such warranties, conditions, offers, promises or assurances, cannot by virtue of law be so excluded.
12. Please note that any claim under this Warranty must be notified to Uni-Pier Australia within a reasonable time after You first noticed or ought reasonably to have noticed the issue/defect. If Uni-Pier Australia is not notified of the claim within a reasonable time of You first noticing the issue/defect, Uni-Pier Australia may in its absolute discretion deny the claim and Uni-Pier Australia shall have no liability under this Warranty.
13. You will bear the expense of ancillary costs associated with making a claim against this Warranty.
14. To initiate a claim under this Warranty, contact Uni-Pier Australia on the details below:

Uni-Pier Australia Pty Ltd ACN 131 900 546  
 Head Office: 188 Silverwater Road Silverwater NSW 2128  
 Post your claim to: PO Box 6484 Silverwater NSW 1811  
 Telephone: 1300 366 362  
 Email: info@unipier.com.au





## ADVISORY NOTE #49.1

### BEST PRACTICE FOR BCA VOLUME 2 PART 3.4.4.4 CORROSION PROTECTION

---

# TABLE OF CONTENTS

## Contents

BEST PRACTICE FOR BCA VOLUME 2 PART 3.4.4.4 CORROSION PROTECTION	1
1. INTRODUCTION	1
2. NATIONAL CONSTRUCTION CODE	2
2.1. Structural steel members in the BCA	2
2.2. Corrosion protection of structural steel members in the BCA	2
3. HOT DIP GALVANIZING	4
4. ENVIRONMENTAL CONDITIONS FOR CORROSION OF STEEL	5
4.1. Corrosion of steel in housing applications	5
4.1.1. The macro-environment	5
4.1.2. Corrosion rate of steel and HDG coatings in the macro-environment	7
4.1.3. The micro-environment	10
5. INCREASING DURABILITY AT THE SOIL/CONCRETE/GALVANIZED STEEL INTERFACE	11
5.1. Embedded structural steel members	11
5.2. Additional barrier protection	12
5.3. Installing posts on elevated concrete pads	14
6. HDG STEEL IN CONTACT WITH TIMBER	15
7. SUMMARY	16
8. REFERENCES	17

*Front Cover: “House in Hamilton” by Phorm Architecture + Design (Australia) and Tato Architects (Japan) using 100% Australian-made steel. This project was an entrant into the Queensland 2016 ASI Steel Excellence Awards and received a Commendation in the 2016 National Architecture Awards: Residential Architecture – Houses (New) category. Image by Christopher Frederick Jones.*

*Other images by Galvanizers Association of Australia and/or its members and courtesy Uni-Pier Australia Pty Ltd.*

*All images are © copyright of the original authors and must not be reproduced without permission.*

---

## BEST PRACTICE FOR BCA VOLUME 2 PART 3.4.4.4 CORROSION PROTECTION

### 1. INTRODUCTION

This Advisory Note provides additional advice to the Building Code of Australia for the corrosion protection of structural steel in housing and related applications. It deals with the common issues but cannot describe all situations and independent professional advice must be sought if there is any doubt.

The National Construction Code 2019 Building Code of Australia – Volume 2 (Amendment 1) (1) sets out the requirements for corrosion protection of certain structural steel members such as:

- Bearers supporting a timber floor or non-loadbearing stud wall
- Strutting beams supporting roof and ceiling loads
- Lintels supporting a roof, ceiling, frame, and timber floor
- Columns

Table 3.4.4.4 of the Building Code of Australia (BCA) sets out the minimum requirements for protective coatings where the degree of corrosion protection is determined by the described environment and location. The BCA rules relating to external environments and the minimum corrosion protection required do not fully describe the corrosivity experienced by structural steel in all common situations and can lead to poor outcomes for service life of the coating and, in some cases, early failure of structural steel members, even if they have been supplied and installed to the requirements of the BCA.

Users should also be aware there are multiple types of coatings that are claimed by their suppliers to be a form of galvanizing. Most of the common coatings available in Australia will not meet the minimum requirements of the BCA, except in moderate internal exposures or with the addition of a paint topcoat. **Only batch hot dip galvanized steel coatings produced to AS/NZS 4680 (2) always meet the minimum requirements of the BCA for structural steel members without the addition of a topcoat.** It is important that the correct specification is selected and supplied to ensure adequate performance of the galvanized coating. In addition, if a paint coating option is selected, the BCA does not provide a full specification and it may be difficult to assess conformance to the requirements of the BCA without an expert opinion.

*Note: This section of the BCA does cover structural steel members used in masonry construction but does not cover corrosion protection of structural steel built into a masonry wall such as lintels. For lintels and other structural steel elements built into masonry, specifiers must refer to AS 3700 (3), the AS 2699 (4) series, and Part 3.3.5 of the BCA.*

This Advisory Note is intended to keep readers abreast of current issues and developments in the field of galvanizing. The Galvanizers Association of Australia has made every effort to ensure that the information provided is accurate, however its accuracy, reliability or completeness is not guaranteed. Any advice given, information provided, or procedures recommended by GAA represent its best solutions based on its information and research, however may be based on assumptions which while reasonable, may not be applicable to all environments and potential fields of application. Due and proper consideration has been given to all information provided but no warranty is made regarding the accuracy or reliability of either the information contained in this publication or any specific recommendation made to the recipient. Comments made are of a general nature only and are not intended to be relied upon or to be used as a substitute for professional advice. GAA and its employees disclaim all liability and responsibility for any direct or indirect loss or damage which may be suffered by the recipient through relying on anything contained or omitted in this publication.

# ADVISORY NOTE #49.1

## 2. NATIONAL CONSTRUCTION CODE

The National Construction Code (NCC) is Australia's primary set of technical design and construction provisions for buildings. It is a self-described performance-based code which primarily applies to the design and construction of new buildings and is used by architects, builders, building surveyors, engineers and other building related professions and trades. The NCC is given legal effect through relevant State and Territory legislation and the applicability of the NCC for a particular situation should be assessed against the relevant local legislation.

The Building Code of Australia (BCA) makes up 2 volumes of the NCC, with Volume 2 the subject of this Advisory Note. Volume 2 primarily covers the design and construction of houses, small sheds, carports, and some other associated structures. The NCC allows either a *Performance Solution* or a *Deemed-to-Satisfy Solution* to meet the requirements of the BCA. The differences can be complex, and these are described in Part A2 of Volume 2 of the BCA.

Part 3 of Volume 2 deals with acceptable construction for Deemed-to-Satisfy Solutions. It is this aspect that is clarified in this Advisory Note. The guidelines in this Advisory Note are not a Performance Solution but do provide more information that will assist professionals in the development of a suitable corrosion protection system for structural steel in some common applications.

### 2.1 Structural steel members in the BCA

A range of structural steel members are included in the Acceptable Construction Practice section of Part 3.4.4 of the BCA. Hot formed sections included are a range of taper flange beams, universal beams, parallel flange channels, taper flange channels, equal angles, and unequal angles. Cold formed sections in the BCA structural steel section include a range of standard tubular sections (rectangular, square, and round hollow sections). Structural steel members covered vary in thickness from 1.6mm for a limited selection of tubular sections to well over 6mm thickness on various hot formed sections. The steel thickness is important as it affects the hot dip galvanized (HDG) coating thickness formed on batch hot dip galvanized sections which, in turn, directly influences the durability of the structural steel member and therefore the durability of the structural steel member.

### 2.2 Corrosion protection of structural steel members in the BCA

The BCA provides for mandatory corrosion protection of structural steel members in Volume 2 Part 3.4.4.4 where two atmospheric environments (*moderate* and *severe*) are described (Table 1 of this document). In addition, the concept of *breaking surf* is introduced, and a definition of *heavy industrial areas* is provided. The BCA does not provide any mandatory requirements related to micro-environments, except where steel in the roof space is exposed to moist exhaust gases from kitchen or bathroom fans.

A *moderate* environment is defined as being more than 1km from breaking surf or more than 100m from salt water not subject to breaking surf or non-heavy industrial areas.

A *severe* environment is defined as being within 1km of breaking surf or within 100m of salt water not subject to breaking surf or heavy industrial areas.

## ADVISORY NOTE #49.1

*Breaking surf* is defined as any area of salt water where waves break on an average of 4 days per week but does not include white caps or choppy water. This normally occurs in open seas and would usually preclude sheltered locations in the vicinity of Port Philip Bay, Sydney Harbour and near coastal rivers such as Derwent, Swan, and Brisbane Rivers.



Figure 1A severe environment located within 1km of breaking surf.

*Heavy industrial areas* are defined as the industrial environments around major industrial complexes. Corrosion of steel from industrial effects is no longer an important factor as heavy industrial areas are relatively few in Australia and are known from surveys to be restricted to the areas nearby to the processing plants at Mt Isa and Port Pirie (see AS 4312 (5) for more information).

Structural steel members in the outer leaf and cavity of an external masonry wall of a building, including walls under open carports are external environments for the purpose of the BCA, while a part of an internal leaf of an external masonry wall which is in the roof space is considered to be in an internal wall. For lintels and other structural steel elements built into masonry, specifiers must use AS 3700, the AS 2699 series, and Part 3.3.5 of the BCA.

Table 1 BCA Volume 2 Table 3.4.4.7 Protective coatings for steelwork

Environment	Location	Minimum protective coating
<b>Moderate</b> <i>More than 1 km from breaking surf or more than 100 m from salt water not subject to breaking surf or non-heavy industrial areas</i>	Internal	No protection required in a permanently dry location
	External	Option 1. 2 coats alkyd primer Option 2. 2 coats alkyd gloss Option 3. Hot dip galvanise to 300 g/m <sup>2</sup> min Option 4. Hot dip galvanise to 100 g/m <sup>2</sup> min <b>plus</b> - 1 coat solvent based vinyl primer; or 1 coat vinyl gloss or alkyd
<b>Severe</b> <i>Within 1 km from breaking surf or more within 100 m from salt water not subject to breaking surf or heavy industrial areas</i>	Internal	Option 1. 2 coats alkyd primer Option 2. 2 coats alkyd gloss
	External	Option 1. Inorganic zinc primer 2 coats vinyl gloss finishing coats Option 2. Hot dip galvanise to 300 g/m <sup>2</sup> min Option 3. Hot dip galvanise to 100 g/m <sup>2</sup> min <b>plus</b> - 2 coats solvent based vinyl primer; or 2 coats vinyl gloss or alkyd

*Additional Notes (from the BCA):*

1. Where a paint finish is applied the surface of the steel, work must be hand or power tool cleaned to remove any rust immediately prior to painting.
2. All zinc coatings (including inorganic zinc) require a barrier coat to stop conventional domestic enamels from peeling.
3. Refer to the paint manufacturer where decorative finishes are required on top of the minimum coating specified in the table for the protection of the steel against corrosion.
4. For applications outside the scope of this table, seek specialist advice.

## ADVISORY NOTE #49.1

The description of paints (alkyd primer, alkyd gloss, solvent based vinyl primer, vinyl gloss and inorganic zinc primer) in the above table are considered by the GAA to be incomplete and unsatisfactory for a specification. This is because there is no coating thickness requirement, the surface preparation requirement is inadequate and will allow the steel surface to be poorly prepared (while conforming to the instructions in note 1 above), often leading to early corrosion, and not all the paint types are available. Users should request a performance solution be prepared if the drawings recommend a painted solution for structural steel members.

### 3. HOT DIP GALVANIZING

Hot dip galvanizing is the process of dipping a structural steel member or fabrication into molten zinc. The process forms a metallurgical bond between the zinc and the steel to create a long lasting and abrasion resistant coating that protects against corrosion in atmospheric conditions. More detail on the process can be found at the GAA's website ([www.gaa.com.au](http://www.gaa.com.au)).

For all hot formed structural steel members (taper flange beams, universal beams, parallel flange channels, taper flange channels, equal angles, and unequal angles), hot dip galvanizing can only be applied by the batch hot dip galvanizing process governed by Australian Standard AS/NZS 4680 (Table 2). Batch hot dip galvanized tubular sections are also covered by AS/NZS 4680. Although other galvanized coating solutions are marketed in Australia, none of the continuous galvanized coatings applied over SHS or RHS tubular sections meet the coating mass and thickness requirements of the BCA without the addition of a paint topcoat.

Table 2 Hot dip galvanized coating thickness requirements for AS/NZS 4680

Steel thickness (mm)	HDG coating thickness average minimum ( $\mu\text{m}$ )	HDG coating mass average minimum ( $\text{g}/\text{m}^2$ )
> 6	85	600
> 3 to $\leq$ 6	70	500
$\geq$ 1.5 to $\leq$ 3	55	390

*Note: The galvanized coating thickness is the usual method of checking compliance of galvanized coating application and can be converted to mass by multiplying by 7.14. The galvanized coating mass is rounded for convenience of description.*

The requirements of AS/NZS 4680 are such that even the thinnest batch HDG coating will exceed the requirements of Table 3.4.4.7 of the BCA, and the actual thickness received will provide for a HDG coating service life significantly more than envisaged in the BCA.

As noted above, other types of hot dip galvanized coatings are readily available for tubular sections and most of these will not meet the minimum requirements for hot dip galvanized steel alone in the BCA (300  $\text{g}/\text{m}^2$ ) and only those hot formed sections which are hot dip galvanized to meet the requirements of AS/NZS 4680 will conform to the BCA. It is critical that the designer specifies the correct material and the builder orders and receives the correct material to ensure long term durability of the coating.

# ADVISORY NOTE #49.1

## 4. ENVIRONMENTAL CONDITIONS FOR CORROSION OF STEEL

### 4.1. Corrosion of steel in housing applications

The corrosion of steel in housing is generally related to the atmospheric corrosivity experienced by steel, known as the macro-environment, plus any localised effects, known as the micro-environment, such as sheltering of unwashed surfaces in corrosive locations, defects in the corrosion protection from steel fabrication or installation, and design defects.

#### 4.1.1. The macro-environment

The general atmospheric condition in an area is usually the main driver affecting the corrosion rate of steel and this is known as the macro-environment. Australian Standards AS 4312 and AS/NZS 2312.2 (6) provide excellent guidance on the macro-environment in Australia.

For ease of design, the macro-environment is generally broken up into Corrosivity Zones. The zones are generally related to the distance from the coast and the type of coast, where the corrosion rate of steel increases dramatically as the distance to the coast decreases (see Figure 2 and Table 3). The type of coast is important, where the conditions around sheltered bays are usually less corrosive, while exposure to surf increases the corrosion rate of steel. Category CX (as described in Table 3) mainly occurs at the shoreline of severe surf conditions and is therefore not generally applicable for domestic housing.




Figure 2 Corrosivity Categories as shown in AS4312 and AS/NZS2312.2



Figure 3 Batch hot dip galvanized structural steel posts in combination with a continuous galvanized sub-floor located in a BCA moderate zone (more than 1km from breaking surf)

# ADVISORY NOTE #49.1

Table 3 Corrosivity in Australia as described in AS 4312 and AS/NZS 2312.2

Category		Generic Examples	Specific Examples
CX	Severe surf shoreline	Surf beach shoreline regions with very high salt deposition.	Some Newcastle beaches
C5	Surf Seashore	Within 200 m of rough seas & surf beaches. May be extended inland by prevailing winds & local conditions.	More than 500 m from the coast in some areas of Newcastle
C4	Calm Seashore	From 200 m to 1 km inland in areas with rough seas & surf. May be extended inland by prevailing winds & local conditions.	All coasts
		From the shoreline to 50 m inland around sheltered bays. In the immediate vicinity of calm salt water such as harbour foreshores.	
C3	Coastal	From 1 km to 10 km inland along ocean front areas with breaking surf & significant salt spray. May be extended inland to 50 km by prevailing winds & local conditions.	Metro areas of Perth, Wollongong, Sydney, Brisbane, Newcastle, & the Gold Coast
		From 100 m to 3 – 6 km inland for a less sheltered bay or gulf.	Adelaide & environs
		From 50 m to 1 km inland around sheltered bays.	Port Philip Bay & in urban & industrial areas with low pollution levels
C2	Arid/Urban Inland	Most areas of Australia at least 50 km from the coast.	Canberra, Ballarat, Toowoomba & Alice Springs
		Inland 3 – 6 km for a less sheltered bay or gulf.	Adelaide & environs
		Can extend to within 1 km from quiet, sheltered seas.	Suburbs of Brisbane, Melbourne, Hobart
C1	Dry indoors	Inside heated or air-conditioned buildings with clean atmospheres.	Commercial buildings

Combining the information from Table 1 (BCA) and Table 3 (AS 4312 and AS/NZS 2312.2), and assuming a conservative position for the change of C4 to C3 at 200m for sheltered coasts, designers can refine the BCA definitions into Moderate C2, Moderate C3, Severe C4 and Severe C5 (Table 4).

# ADVISORY NOTE #49.1

Table 4 Comparison of distance from salt water for BCA and AS 4312

BCA Table 3.4.4.7 (External Locations)			AS 4312		
Environment	Specified distance from salt water		Corrosivity category	Typical distance from salt water	
	Surf coast	Sheltered coast		Surf coast	Sheltered coast
Moderate	>1km	>100m	C2	>50km	>10km
				10km to 50km	1km to 10km
			C3	1km to 10km	50m to 1km
Severe	≤1km	≤100m	C4	200m to 1km	<50m
			C5	<200m	N/A

The distance of C2 and C3 zones from the coast do vary around Australia, and this can influence the best solution for corrosion protection. More importantly, the severe zone defined in the BCA covers a very wide range of corrosion rates for steel and galvanized coatings, directly influencing the durability of the solution. The GAA recommends that designers take the time to understand the distance of the house or structure from corrosive influences before deciding on the coating solution. This is discussed further in the next section.

## 4.1.2. Corrosion rate of steel and HDG coatings in the macro-environment

The rate of corrosion for uncoated structural steel members and HDG coatings is provided by AS 4312 and AS/NZS 2312.2 (Table 5). The corrosion rate can be compared to standard HDG coating thicknesses to determine the estimated service life of the HDG coating. Using this information and the options available in Table 3.4.4.7 of the BCA, the estimated service life of each option can be determined.

Table 5 Rate of corrosion of structural steel and HDG coatings

Corrosivity category, (AS 4312 & AS/NZS 2312.2)	description & typical environment	Structural steel members	HDG coatings
		Typical corrosion rate for	the first year (µm/y)
C1	Very low Dry indoors	≤1.3	≤0.1
C2	Low Arid/Urban inland	>1.3 to ≤25	>0.1 to ≤0.7
C3	Medium Coastal	>25 to ≤50	>0.7 to ≤2.1
C4	High Calm seashore	>50 to ≤80	>2.1 to ≤4.2
C5	Very High Surf seashore	>80 to ≤200	>4.2 to ≤8.4
CX	Extreme Ocean/Offshore	>200 to ≤700	>8.4 to ≤25

The corrosion rates shown in each Corrosivity Category of Table 5 are provided as a range where, for normal Australian washed atmospheric exposures, the distance from the coast is the driving force.

Table 6 shows the same information in the form of life to first maintenance of the galvanized coating and also shows the BCA minimum galvanized coating requirement as a comparison. For galvanized coatings this should be considered the time at which major maintenance of the item is required to reinstate corrosion protection to the steel.

# ADVISORY NOTE #49.1

Table 6 Expected range of life to first maintenance of HDG coatings in the macro-environment for commonly available corrosion protection methods according to AS/NZS 2312.2

Product and type		Steel thickness	HDG coating mass & thickness		Corrosive category & calculated life of galvanised coating (min-max, years)			
		mm	g/m <sup>2</sup>	µm	C2	C3	C4	C5
BCA Table 3.4.4.7	HDG 300 g/m <sup>2</sup>	All	300	42	60->100	20-60	10-20	5-10
AS/NZS 4680	HDG390	>1.5-≤3.0	390	55	78->100	26-78	13-26	6-13
	HDG500	>3.0-≤6.0	500	70	>100	33-100	16-33	8-16
	HDG600	>6.0	600	85	>100	40->100	20-40	10-20
AS/NZS 4792 <sub>1</sub>	ZB100/100	All	100	14	20->100	6-20	3-6	1-3
	ZB135/135	All	135	19	27->100	9-27	4-9	2-4
AS 4750 <sub>2</sub>	ZE50	All	50	7	10-70	3-10	1-3	0-1

**Notes:**

- AS/NZS 4792 (7) galvanized coatings are only available for cold formed tubular sections and use pre-galvanized strip which is then formed into a welded tube. The welded area is repaired by the tube manufacturer to restore corrosion protection to the AS/NZS 4792 Standard. Any subsequent fabrication will also require repair to this Standard.
- AS 4750 (8) ZE50 is the Australian Standard for electrogalvanized tubular sections commonly available in Australia. While the coating mass (50 g/m<sup>2</sup>) does not meet the minimum requirements of the BCA for hot dip galvanizing before paint topcoats are applied, the life of the electrogalvanized coating according to AS/NZS 2312.2 is included here for information. Electrogalvanized coatings are also not strictly hot dip galvanized as the coating is mechanically bonded to the underlying steel and does not form the hard, abrasion resistant zinc-iron alloy layers formed by other galvanized methods. These coatings would generally be only suitable for internal applications or with an engineered performance solution with additional paint coatings.

Using the data in Table 6, the BCA provides for conforming products with as little as 5 years galvanized coating life (HDG 300 g/m<sup>2</sup>) in a severe (C5) environment, and over 100 years for the same product in a moderate (C2) environment. While complete consumption of the galvanized coating after 5 years does not mean the structural failure of the steel member, it would almost certainly attract the ire of most homeowners, purely on appearance. A simple extrapolation of the corrosion rates for steel indicates the structural steel member, once fully exposed in the top end C5 environment, loses 1mm of section on each exposed face in 5 years, and this certainly provides a risk of structural failure. The two questions that then need answering are:

1. What is an acceptable life for the coating and the structural member?
2. What maintenance to the galvanized coating can be reasonably expected by a homeowner?

To answer these questions, we need to understand the accessibility of the member for maintenance, the difficulty in providing the required maintenance and/or the cost of simply replacing the member.

## ADVISORY NOTE #49.1

Examples of structural steel members which are generally not accessible or economical to replace are floor piers/stumps embedded in concrete and load bearing steel members within the building envelope. These structural members should reasonably be expected to last 50 years, or the life of a normal building, with minor maintenance of the accessible areas.

Examples of structural steel members which have moderate ease of access but are difficult or costly to repair include floor piers/stumps which are bolted to a base plate or attached to, but not embedded in, a concrete footing. These structural members should reasonably be expected to last 15 years with minor maintenance including regular maintenance of the coating. A house on tall piers will be easier to maintain than one where the piers are close to the ground and a degree of common sense is required.

Examples of structural steel which is **readily accessible and economical** to maintain or replace include verandah posts. However, if the verandah post is embedded into a tiled verandah (figure 4), corrosion may occur due to a micro-environment (see section 4.1.3) out of sight of the homeowner and failure could occur relatively early in the expected structural life.



Figure 4A verandah post embedded into a tiled floor in a wet area. Water has seeped into the gap between the tile and the steel through capillary action, leading to accelerated corrosion and early failure. This is a design defect where separation of the water from the steel was not considered.



Figure 5 The galvanized structural steel members (verandah posts and edge members) have good access and would be expected to provide structural support with regular maintenance of the galvanized coating for 50 years in moderate locations, while regular maintenance, plus repairs to the galvanized coating would be expected during the life of the building in severe environments.

## ADVISORY NOTE #49.1

### 4.1.3. The micro-environment

Buildings are known to offer a shielding effect when the steel is fully enclosed, and the corrosion rate of steel when it is fully enclosed (for example, in the dry roof space of a house) is very low, even in the harshest of external environments.

If the steel is not fully enclosed in the building and is exposed to wind-driven salt in an area which is not exposed to cleansing rain (for example a beam under a verandah or an edge column of a subfloor), the corrosivity of the micro-environment can be significantly higher than the overall, or macro-environment. This aspect is critical for estimating the design life of structural steel. The BCA instructs designers to consider structural steel members in the outer leaf and cavity of an external masonry wall of a building, including walls under open carports as external environments, while a part of an internal leaf of an external masonry wall which is in the roof space can be considered to be in an internal wall. This means that the tops of verandah posts should be generally considered external, as should any structural members in the open roof space of an open carport.

Design of the ground/steel interface is also critical as ponding of moisture can significantly accelerate the corrosion of the coating and the structural steel. This effect is known as *ring barking* or *collar corrosion* and is common where water or moisture can pond at the base and in areas where water can seep into gaps around the steel post and soil, concrete, paved, or tiled joints.

Defects in the corrosion protection can also lead to accelerated corrosion. For example, this can occur when hot dip galvanized steel has been welded and not properly repaired, or when a painted steel member has had the paint coating damaged on installation or during use, or when the paint used was not appropriately specified and applied.



Figure 6 The top floor of this house overlooking the ocean is enclosed, while the underside of the balcony is open providing for different micro-environments in the same house. In addition, the plants may offer sheltering from rain but not wind-blown salt, leading to a complex corrosion design.



Figure 7 This large post bolted to a concrete pad will finish below the ground level and will be at risk of collar corrosion reducing the durability of the structure.

## ADVISORY NOTE #49.1

### 5. INCREASING DURABILITY AT THE SOIL/CONCRETE/GALVANIZED STEEL INTERFACE

The galvanized steel to concrete and galvanized steel to soil interface is a common site of accelerated corrosion in external environments, especially when the corrosivity of the local micro-environment is C3 or higher. This failure is known as ring barking or collar corrosion. Numerous steps can be taken to help a galvanized steel member embedded in concrete and soil reach the desired service life. Some or all the following measures may be required depending on the corrosivity of atmospheric environment and potential issues identified during the design process.

#### 5.1. Embedded structural steel members

If water can pool at the interface between the galvanized steel and concrete or soil, a localised corrosion cell forms which results in higher-than-expected corrosion rates. Ponding can be minimised by building up concrete or soil around the interface to promote a natural water run-off, and by preventing water from running down the member to the interface. If ponding cannot be avoided through a design change, additional barrier protection is recommended at the interface. Figure 8 shows examples of the range from best to worst protection of the galvanized coating in soil and concrete.




Figure 8 Showing the best design (left) to worst design (right) for galvanized steel embedded in soil and concrete. See also Figure 11 for more details on the best design practice for posts embedded in concrete in a corrosive location.

## ADVISORY NOTE #49.1

### 5.2. Additional barrier protection

Hot dip galvanized structural steel members are embedded in concrete footings to extend life and provide a higher tolerance to the overturning moment. For this design to be effective the concrete/steel/air interfaces must be designed and built correctly. This includes extending the concrete below the bottom of the pier, according to the Engineers specification, ensuring the concrete extends above the natural ground level and slopes away from the steel by at least 10° to prevent ponding, and adding additional barrier protection when the exposed atmospheric corrosivity category is C3 or above (Figure 10 and Figure 11). This method is especially useful when long-term corrosion protection is required in a corrosive atmosphere and for housing posts, piers or stumps which are at the perimeter of a sub-floor.



Figure 9A galvanized post without additional protection at the steel and concrete interface showing accelerated corrosion which has reduced the overall durability of the structure. Note the galvanized coating above the ground remains in excellent condition.

Concrete, bricks, and mortar are susceptible to corrosion in acid sulphate soils and will not provide significant protection in these circumstances unless the concrete is designed for these soils. The best solution is to modify the fill and/or increase the cover if concrete use is required (see also GAA Advisory Note AN 42 (9)). If the concrete footing finishes below the finished ground level, then the protection of the galvanized steel to soil interface with a barrier coating is always recommended to increase the durability of the steel structure.



Figure 10 Denso Ultraseal tape wrapped around the base of a newly embedded post.

There are several options for protecting the galvanized steel with an additional barrier at the galvanized steel and concrete or soil interface. The normal methods are by using a suitably thick paint or tape wrapping, such as Denso “Ultraseal” cold applied bituminous tape (10) (Figure 10). Tapes and paint allow the concrete base to end at or below the interface to the atmosphere, but it will be necessary to consider the corrosivity of the soil in these designs. The barriers are also more susceptible to accidental damage in use. For this application, while probably more expensive than a paint coating, the Denso Ultraseal is easier to apply in the field than other tapes, faster to apply than paint coatings with little to no curing time and has the additional benefit of being able to be selectively overcoated where required.




Figure 11 Recommended design for protection of steel to concrete interfaces for long-term durability.

As noted above, there are several suitable alternative solutions for barrier coatings and the best solution will vary depending on the exposure environment, aesthetic requirements, and availability of materials. If the micro-environment is C3 or higher, including an aggressive internal location, the GAA recommend embedding the steel in concrete and:

1. Apply to at least 100mm above the finished height of the concrete or soil and at least 250mm below the concrete:
  - a. a non-conductive abrasion resistant high build epoxy paint layer at approximately 350µm dry film thickness (DFT) without zinc or aluminium pigment (AS/NZS 3750.14 (11)), or
  - b. Denso Ultraseal tape wrapped around the structural steel section
2. Slope the concrete surface away from the steelwork to facilitate drainage of water away from the steel to concrete interface
3. Once the concrete has cured apply an elastomeric sealant around the interface of the concrete to seal any existing shrinkage cracks

## ADVISORY NOTE #49.1

### 5.3. Installing posts on elevated concrete pads

An alternative to embedding structural steel into concrete footings is to bolt the steel to concrete pads. This means that there is no chance of collar corrosion but does introduce other corrosion design issues that need to be resolved.

The underside the base plate needs to be protected to ensure water is not drawn into the inevitable gap between the galvanized steel base plate and concrete pad. This can be done using a suitably thick epoxy paint coat on the underside of the base plate or a plastic spacer.

A base plate will be either welded or bolted to the upright steel section. In the welded case this should be done before galvanizing to ensure the best protection of the welded area, or the welded areas will need repair with a suitable zinc-rich paint. Almost certainly a post-galvanized welded area will require more regular maintenance, so this should not be done unless access to the repaired area is easy or the welded area is in a very low corrosion area (that is, internal to the building). For bolted connections, all swarf from drilled holes needs to be removed to avoid unsightly rust spots and any cut structural steel will also need to have bare steel repaired to avoid edge corrosion. For tubular sections exposed to rainwater it may also be necessary to seal the joint at the top and between the base plate and the tube with an elastomeric sealant to stop water entry.



Figure 12 A galvanized steel subfloor (with inbuilt ant caps) where the hot dip galvanized posts bolted down onto elevated concrete pads.

## ADVISORY NOTE #49.1

### 6. HDG STEEL IN CONTACT WITH TIMBER

In structural applications in atmospheric or embedded conditions, galvanized steel may be required to be isolated from timber through suitable paints, wraps or other isolating barriers to increase the durability. A common application here is as I-beam or channel retaining wall posts with timber sleepers, where the timber facing elements are painted with an isolating paint.

The Engineered Wood Products Association of Australia <sup>(12)</sup> says timber products treated with cured copper-based preservatives (ACQ, CCA, CuAz) are suitable for use with galvanized steel where the building is protected by a eave overhang of minimum 600mm, average rainfall does not exceed 1000mm (e.g. Melbourne, Adelaide & Perth but not Sydney or Brisbane) and the building or structure is designed and built to exclude 'moisture traps' both during erection and in subsequent use.

Boron treated timber is suitable for indoor applications only and galvanized steel of all types is well suited for use in this application.

LOSP treated products are excellent for use with galvanized steel, although exposure of products to coastal areas will reduce durability of the structure and is not recommended.

HDG steel is not recommended for use to support decks in the wet zones around salt water pools due to the high risk of salt saturated wet timber resulting in accelerated corrosion of the galvanized coating and structural steel.

## ADVISORY NOTE #49.1

### 7. SUMMARY

The BCA sets out the minimum requirements for corrosion protection using protective coatings for structural steel members. Hot dip galvanized coatings of 300 g/m<sup>2</sup> are identified as the minimum requirements for an unpainted structural steel member in external moderate and severe environments.

Only hot dip galvanized coatings meeting the requirements of AS/NZS 4680 can meet the requirements of the BCA without the addition of paint topcoats. Maintenance of the galvanized coating will be required in some environments to maintain structural performance.

A moderate environment covers both C2 and C3 Corrosivity Categories, while the severe environment includes the C4 and C5 Corrosivity Categories. Additional protection will be required for housing located in the C5 Corrosivity Category (that is severe environments within 200m of surf) and may also be required when accessibility for maintenance is impossible or difficult and the local environment is also severe.

For house piers and other structural steel embedded in the ground, additional barrier protection of the galvanized coating is required at the concrete interface, extending 100mm above and 250mm below the concrete surface. In addition, the bottom of the pier should be fully encased in concrete according to the engineer's specification, and the top of the concrete sloped to prevent ponding.

## 8. REFERENCES

1. **Australian Building Codes Board.** *NCC 2019 Building Code of Australia.* Amendment 1. Canberra : (C) Commonwealth of Australia and the States and Territories 2020 Published by the Australian Building Codes Board, 2019. Vol. 2.
2. **Standards Australia & New Zealand Standards.** *Hot dip galvanized (zinc) coatings on fabricated ferrous articles.* Sydney & Wellington : Standards Australia & New Zealand Standards, 2006. AS/NZS 4680.
3. **Standards Australia.** *Masonry Structures.* Sydney : Standards Australia, 2018. AS 3700.
- 4.—. *Built-in components for masonry construction (3 parts).* Sydney : Standards Australia, 2020. AS 2699.
- 5.—. *Atmospheric corrosivity zones in Australia.* Sydney : Standards Australia, 2019. AS 4312.
6. **Standards Australia & New Zealand Standards.** *Guide to the protection of structural steel against atmospheric corrosion by the use of protective coatings, Part 2: Hot dip galvanizing.* Sydney & Wellington : Standards Australia & New Zealand Standards, 2014. AS/NZS 2312.2.
7. **Standards Australia and Standards New Zealand.** *Hot-dip galvanized (zinc) coatings on ferrous hollow sections, applied by a continuous or a specialized process.* Sydney & Wellington : Standards Australia and Standards New Zealand, 2006. AS/NZS 4792.
8. **Standards, Australian.** *Electrogalvanized (zinc) coatings on ferrous hollow and open sections.* Sydney : Standards Australia, 2003. AS 4750.
9. **Galvanizers Association of Australia.** Technical Publications (Advisory Notes). *Galvanizers Association of Australia.* [Online] [Cited: 21 January 2021.] <https://gaa.com.au/technical-publications/>. AN 42.1 Hot dip galvanized steel embedded in soil.
10. **Denso.** Denso Ultraseal Tape. [Online] [Cited: 21 January 2021.] <http://densoaustralia.com.au/pdfs/DensoBitumenButylTapes/Denso-Ultraseal-Tape.pdf>.
11. **Standards Australia and Standards New Zealand.** *Paints for steel structures High-build epoxy (two-pack).* Sydney & Wellington : Standards Australia and Standards New Zealand, 1997 (R 2013). AS/NZS 3750.14.
12. **Engineered Wood Products Association of Australia.** Suitable Fasteners, Metal Flashings, Studs and Joists for use in Conjunction with EWPA Branded Preservative Treated Cladding, T&G Flooring and Structural Plywood. [Online] [Cited: 15 February 2015.] <https://ewp.asn.au/technical-resources>.